
	Material Specification		
	NUMBER AX-122	REV C	SHEET 1 of 3


TITLE: Wire, Nickel, Round Alloy UNS N02200 (Nickel 200)	WRITTEN BY: J.B. 10/16/89	
	ENG APPROVAL: J.B. 10/16/89	
THIS DOCUMENT IS THE PROPERTY OF ANDREX, INC. THIS IS PROPRIETARY INFORMATION AND SHALL NOT BE REPRODUCED OR USED FOR MANUFACTURING, EXCEPT AS MAY BE OTHERWISE PROVIDED BY CONTRACT.	CAGE CODE 2W880	QC APPROVAL: JRHorn 10/16/89

<u>Revision</u>	<u>Description</u>	<u>Date</u>	<u>Approved</u>
-	Release to Production	10/16/89	J.B.
A	ECN-H-107: 115,000-140,000 Tensile Strength was 110,000-130,000	04/14/93	W.M.B.
B	ECN-H176: Revised to add dash numbers for each size.	01/26/99	W.M.B.
C	ECN-H197: Added Tensile Strength column to Table I; in para 3.2, Tensile Strength: "see Table I" was "115,000- 140,000"		

	Material Specification		
	NUMBER AX-122	REV C	SHEET 2 of 3

1. SCOPE.

- 1.1 Scope. This specification defines the requirements for round nickel wire for use in the production of hose and conduit.
- 1.2 Classification. Part Numbers under this specification are coded as follows:



2. APPLICABLE DOCUMENTS.

This section does not apply to this specification.

3. REQUIREMENTS.

Material shall be nickel 200 per UNS N02200 as specified herein.

3.1 Chemical Analysis Requirements:


C:	0.15% max.
Cu:	0.25% max.
Fe:	0.40% max.
Mn:	0.35% max.
Ni:	99.0% min.
S:	0.01% max.
Si:	0.35% max.

3.2 Physical Analysis Requirements:

Cold Drawn
Tensile Strength: See Table I
Elongation: To be satisfied by tests on initial lots submitted by suppliers and run on Andrex Inc. braiders. When satisfactory, supplier shall maintain such controls as are necessary to furnish substantially the same material on all future orders.

TABLE I

Size Identifier	Diameter	Tensile Strength
-008	.0080 ±.0005	115,000-140,000 psi
-011	.0110 ±.0005	115,000-150,000 psi
-013	.0130 ±.0005	115,000-150,000 psi

	Material Specification		
	NUMBER AX-122	REV C	SHEET 3 of 3

3.3 Material Workmanship:

Wire shall be clean, smooth, free from defects or surface imperfections and carefully coiled without kinks.

4. QUALITY ASSURANCE PROVISIONS.

4.1 Quality Assurance shall be responsible for inspection of material upon receipt of each lot for conformance to this specification, or unless otherwise specified by any requirements stated on the lot's specific purchase order.

5. PREPARATION FOR DELIVERY.

5.1 Spooling Requirements:

Vendor shall supply continuous lengths of wire on spools having 1-1/4" I.D. Bore and 8" O.D. Flange. Approximate weight should be 30 lbs. per spool. Spools shall have 10 lbs. min of wire. Spool traverse shall be approximately 6 inches. Spooling shall be such that wire may be unwound under reasonable tension without binding.

5.2 Supplied on our Braider Bobbins

Supply continuous length on Flexco supplied bobbins with minimum weight of 2.0 lbs. per bobbin. Bobbins shall be wound to insure smooth and even unwinding of bobbin.

5.3 Packaging and Marking:

Packing shall be adequate to protect the spools and wire from contamination and physical damage during shipment. Each spool shall be plainly marked with material identification, wire diameter, shipping date, weight and name of manufacturer. Packaging shall be adequate to insure spooling integrity during shipment.

5.4 Certification:

Certificate of Compliance and Analysis Test Reports must accompany each shipment.

6. NOTES.

6.1 Ordering Information: Purchase orders should specify the following:

- a. Part Number including size identifier (see 1.2)
- b. Description
- c. Quantity, total poundage.
- d. Delivery Date